



FLEXIBLE PVC
FOR EXTRUSION

FLEXIBLE PVC

FOR EXTRUSION

		Density	Hardness	Tensile Strength	Elongation at Break	Cold Flex
Product range		ISO 1183 gr/cc	ISO 868 Shore A	ISO 527 N/mm2	ISO 527 %	ISO 458/2 C°
NON TRASPARENT GRADES						
SA 50 CZ	Gaskets	1,20	50	≥12	≥430	
SA 54 CZ	Window Gaskets	1,33	53	≥9	≥400	
LG 55 CZ N2	Gaskets	1,47	56	≥5	≥340	
LG 58 CZ N1	Agricultural ligature	1,30	57	≥11	≥44	
LG 57 CZ E N	Agricultural ligature	1,49	58	≥6	≥36	
LG 60 CZ N1	Window Gaskets	1,34	60	≥11	≥390	
LG 61 CZ N	Agricultural ligature	1,41	61	≥8	≥380	
SA 63 BZ UV ANI	Agricultural tensioner anti UV	1,26	62	≥14	≥370	
SA 64 AT DT	Pipes and profiles Phthalates free	1,24	64	≥16	≥360	
SA 70 A N1	Pipes and profiles	1,35	70	≥15	≥330	
SA 70 CZ UV	Outdoor profiles anti UV	1,42	70	≥14	≥360	
SA 70 CZ KA N1	Various profiles and pipes	1,43	70	≥12	≥300	
CX 3 M CP D	Spiral pipes	1,25	71	≥17	≥420	
SA 75 A N	Pipes and profiles	1,30	74	≥17	≥350	
SR 75 CZ D	Various profiles and pipes	1,44	75	≥12	≥320	
SA 77 CZ TP N1	Flat extrusion	1,38	77	≥16	≥300	
FB 80 CZ H	Belt conveyor	1,23	80	≥14	≥330	
SA 85 TG AT	Gas hose	1,50	85	≥14	≥250	
SA 88 A N2	Mud flaps	1,40	86	≥16	≥290	
SA 87 CZ M	Various profiles	1,47	87	≥15	≥270	
SA 89 A @ UV	Outdoor profiles anti UV	1,39	89	≥19	≥330	
SL 92 K A C N1	Fancing	1,30	92	≥21	≥280	
CO K CZ N	Semi rigid extrusion	1,39	98			
STOPPER CZ P	Extruder cleaning	1,51	72(SHD)	≥31	≥80	



Via Trani 177 – 76121 BARLETTA (BT)
Tel. +39 0883 34 18 111

PEC: stircompounds@exepec.com
www.stircompounds.it

FLEXIBLE PVC

FOR EXTRUSION

Product range

TRANSPARENT GRADES

		Density	Hardness	Tensile Strenght	Elongation at Break	Cold Flex
		ISO 1183 gr/cc	ISO 868 Shore A	ISO 527 N/mm2	ISO 527 %	ISO 458/2 C°
T 2054 A N	Profiles	1,16	53	≥11	≥460	
T 55 NT DT	Pipes Phthalates free	1,16	55	≥14	≥400	
T 2199 A N UV	Profiles UV resistant	1,16	57	≥13	≥480	
T 2599 A HX	Profiles Phthalates free	1,16	61	≥14	≥460	
T 70 A C SAT N	Satined profiles	1,19	68	≥13	≥300	
T 70 NT DT	Food contact pipes Phthalates free	1,21	70	≥18	≥390	
T 70 A OIL	Gasoline resistant pipes	1,28	70	≥20	≥380	-30
T 4099 AN 1	Pipes	1,20	71	≥18	≥370	
T 71 NT DT UV INT	Anti bacterial profiles UV resistant	1,21	71	≥18	≥360	
T 75 NT DT	Food contact pipes Phthalates free	1,21	75	≥20	≥380	
T 77 TP SN	Flat extrusion	1,22	77	≥19	≥320	
T 78 A FR N	Pipes low temperature	1,23	78	≥20	≥370	
BZ 78 UV AF	Agricultural flexible sheets flame retardant	1,27	79	≥21	≥350	
T 80 BZ AF	Profiles flame retardant	1,30	80	≥20	≥350	
T 80 NT DT	Food contact pipes Phthalates free	1,23	80	≥20	≥360	
BZ 84 UV K8 N	Agricultural flexible sheets	1,23	82	≥21	≥400	
T 5599 A N	Pipes	1,22	83	≥22	≥350	
T 87 NT DT	Saliva ejectors	1,25	87	≥22	≥330	
T 90 CZ DT	Profiles Phthalates free	1,25	90	≥22	≥350	
T 96 NT N	Profiles	1,27	95	≥24	≥300	



Via Trani 177 – 76121 BARLETTA (BT)
Tel. +39 0883 34 18 111



PEC: stircompounds@exepec.com
www.stircompounds.it

FLEXIBLE PVC

FOR EXTRUSION

		Density	Hardness	Tensile Strenght	Elongation at Break	Cold Flex
Product range		ISO 1183 gr/cc	ISO 868 Shore A	ISO 527 N/mm2	ISO 527 %	ISO 458/2 C°
Special blends						
T GUM 44 ATC FR N	Hydrocarbon resisting tubes (PVC+NBR)	1,12	44	≥9	≥490	
T GUM 58 A N	Profiles modified with rubber (PVC+NBR)	1,16	58	≥13	≥410	-30
T GUM 77 ATC N	Pipes modified with rubber (PVC+NBR)	1,21	75	≥17	≥350	
SA 82 CZ PU	Variuos profiles and pipes (PVC+PU)	1,29	82	≥22	≥400	
T GUM 86 BZ K8	Tubes for hot water	1,22	87	≥21	≥350	

STORAGE

These compounds must be stored at ambient temperature (not exceeding 30°) in closed and unbroken packaging in order to avoid exposure to sunlight and water absorbation.

Packaging

Available in 25kg plastic bags, carton oktabins or in silos truck

Notes

The values shown in these tables are typical values obtained from measurement made on extruded samples or pressed plates. The information shown in this document should be considered given simply as a guide for the use of the interested product. The techical information shown derive from our laboratory tests and are indicative and not strictly binding. Stir Compounds s.r.l. so will never be considered responsible for the results obtained by using its products in other production processes.



 Via Trani 177 – 76121 BARLETTA (BT)
 Tel. +39 0883 34 18 111

 PEC: stircompounds@exepec.com
 www.stircompounds.it