



CABLE INDUSTRY

CABLE INDUSTRY

| | Classification | | | | Density | Hardness | Tensile Strength | Elongation at Break | Oxygen Index | Thermal Stability | Cold Flex |
|--|--|--------------|----------|--------|----------------------|----------|------------------|---------------------|--------------|-------------------|-----------|
| | EN 50363-0 | EN 50363-4-1 | VDE 0207 | Others | | | | | | | |
| Sheathing | | | | | | | | | | | |
| General purposes | | | | | | | | | | | |
| SA 62 A C | Sheathing music instruments | | | | 1,36 | 62 | ≥10 | ≥380 | | | |
| SA 67 CZ K8 D2 N | Opaque sheathing | | | | 1,47 | 68 | ≥11 | ≥290 | | | |
| FB 70 CZ FR UV | Low temperature cables | | | | 1,29 | 70 | ≥17 | ≥350 | | | -45 |
| SA 70 R CZ N1 | General purposes | | | | 1,46 | 70 | ≥10 | ≥330 | | ≥40 | |
| SR 75 REF CZ N | General purposes | | | | 1,47 | 74 | ≥10 | ≥290 | | ≥40 | |
| SG 79 A OIL C | Hydrocarbons and oil resistant | | | | 1,36 | 75 | ≥13 | ≥420 | | ≥70 | -40 |
| SG 78 CZ OIL | Oil resistant | | | | 1,43 | 78 | ≥16 | ≥300 | | | |
| SR 78 GUA CZ D2 | General purposes | | | | 1,45 | 78 | ≥12,5 | ≥250 | | | |
| FB 81 CZ N1 | Sheathing Coaxial TV Cable | | | | 1,35 | 81 | ≥17 | ≥300 | | | |
| SR 80 CZ GK N RAT | Anti rodent and termites | | | | 1,52 | 82 | ≥13 | ≥300 | | | |
| SR 83 GUA CZ N4 | General purposes | | | | 1,49 | 82 | ≥12,5 | ≥250 | | ≥60 | |
| SA 86 A C1 N | General purposes | | | | 1,49 | 86 | ≥13 | ≥280 | | ≥60 | |
| Flame-Retardant Sheathing | | | | | | | | | | | |
| AF SG 79 A OIL C | Hydrocarbons and oil resistant sheathing | | | | UL 1581 Classe 43 | 1,36 | 75 | ≥13 | ≥440 | 25,5 | ≥70 |
| AF 79 CZ EL N | General purposes (SUGGESTED FOR CPR APPLICATIONS) | | | | R18 | TM2 | 1,54 | 81 | ≥13 | ≥290 | 30 |
| AF 82 CZ BL 1 | General purposes | | | | | TM1 | 1,54 | 82 | ≥13 | ≥280 | 30 |
| AF 83 CZ ZB N | General purposes (SUGGESTED FOR CPR APPLICATIONS) | | | | R18 | TM2 | 1,59 | 84 | ≥12 | ≥270 | 29 |
| AF 88 2 CZ MAHY | General purposes (SUGGESTED FOR CPR APPLICATIONS) | | | | R16 | | 1,62 | 86 | ≥13,5 | ≥250 | 36 |
| AF 86 CZ | FRLS cables (Hcl ≤16%) | | | | | TM1 | 1,46 | 86 | ≥15 | ≥280 | 29 |
| AF SG 88 A OIL C | Hydrocarbons and oil resistant sheathing | | | | | TM5 | 1,39 | 87 | ≥17 | ≥360 | 27,5 |
| Sheathing for high temperatures | | | | | | | | | | | |
| AF SG 76 HT 105 CZ OIL | Operating temperature 105°C (Oil resistant) | | | | UL 1581 Classe 43 | TM5 | 1,39 | 76 | ≥16 | ≥240 | 28 |
| SR 77 HT 90 CZ | Operating temperature 90°C | | | | | TM3 | 1,36 | 77 | ≥14 | ≥240 | ≥240 |
| SR 79 HT 105 CZ TM | Operating temperature 105°C | | | | | | 1,38 | 79 | ≥14 | ≥240 | ≥240 |
| AF SG 84 HT 90 CZ OIL | Operating temperature 90°C (Oil resistant) | | | | UL 1581 Classe 43 | TM5 | 1,50 | 84 | ≥15 | ≥240 | 28 |

CABLE INDUSTRY

| | | Classification | | | | Density ISO 1183 gr/cc | Hardness ISO 868 Shore A | Tensile Strength ISO 527 N/mm2 | Elongation at Break ISO 527 % | Oxygen Index ISO 4589 % | Thermal Stability CEI 20-34/3-2 Minutes | Cold Flex ISO458/2 C° | Volume Resistivity @23°C ASTM D 257Ω cm |
|---|--|----------------|---------------|------------------------|--------------------|------------------------------|--------------------------------|---|--|----------------------------------|---|--------------------------------|---|
| | | EN 50363-0 | EN 50363-3 | VDE 0207 | Others | | | | | | | | |
| Insulation | | | | | | | | | | | | | |
| General purposes | | | | | | | | | | | | | |
| SR 82 FR CZ | Low temperature insulation | | | T14 | 1,26 | 82 | ≥18 | ≥380 | | | | | |
| SR 90 CZ D KA | General purposes | | | T12 | 1,59 | 90 | ≥11 | ≥200 | | | | | |
| SR 91 FAC CZ 1 | Telephone Cables | | | T1 | 1,36 | 90 | ≥17 | ≥300 | | ≥100 | | 1X10 ¹⁴ | |
| SR 90 CZ LIB | General purposes | | | Y14 | 1,46 | 90 | ≥16 | ≥280 | | ≥120 | -40 | | |
| SR 90 CZ GC | General purposes | | | HD602DIV4 | 1,47 | 90 | ≥14 | ≥280 | | ≥120 | | | |
| SR 90 CZ N | General purposes | | | T1 | 1,51 | 90 | ≥15 | ≥200 | | ≥60 | | 9X10 ³ | |
| SR 90 CZ EL D1 | General purposes | | | Y11 Y12 | 1,54 | 90 | ≥14 | ≥240 | | ≥50 | -30 | 8X10 ³ | |
| Flame-Retardant insulation | | | | | | | | | | | | | |
| AF 91 A C ZB | General purposes | | | R2 | IEC60332-3 1,51 | 89 | ≥14 | ≥260 | 29 | ≥50 | -23 | | |
| AF 90 CZ ZB CE | General purposes (SUGGESTED FOR CPR APPLICATIONS) | | | S18 | 1,57 | 90 | ≥15 | ≥240 | 29 | | | | |
| AF 90 CZ ZB CE3 | General purposes (SUGGESTED FOR CPR APPLICATIONS) | | | S17 | 1,44 | 90 | ≥16 | ≥240 | 30 | | | | |
| AF 92 CZ BL | General purposes | | | T11 | 1,55 | 92 | ≥16 | ≥240 | 32,5 | | | | |
| AF 96 CZ ZB | General purposes | | | T11 | 1,58 | 96 | ≥13 | ≥220 | 29 | | | | |
| Insulation for high temperatures | | | | | | | | | | | | | |
| SR 90 HT 90 CZ D | Operating temperature 90°C (automotive) | | | ISO 6722-1 Classe A | 1,31 | 90 | ≥16 | ≥280 | | ≥240 | | | |
| SR 91 HT 90 CZ5 | Operating temperature 90°C | | | T13 | 1,39 | 91 | ≥14 | ≥230 | | ≥240 | | 1X10 ¹⁴ | |
| SR 92 HT 105 CZ C | Operating temperature 105°C (automotive) | | | ISO 6722-1 Classe B | 1,34 | 92 | ≥16 | ≥280 | | ≥300 | | 1X10 ¹⁴ | |
| SR 94 HT 105 CZ1 | Operating temperature 105°C | | | | 1,40 | 94 | ≥19 | ≥270 | 26 | ≥300 | | 1X10 ¹⁵ | |
| SR 96 HT 125 K8 CZ C | Operating temperature 125°C (automotive) | | | ISO 6722-1 Classe C | 1,29 | 96 | ≥20 | ≥260 | | ≥420 | | 1X10 ¹⁴ | |

CABLE INDUSTRY

| Classification | | Density | Hardness | Tensile Strength | Elongation at Break | Oxygen Index | Thermal Stability | Cold Flex |
|----------------|--------|----------------|-----------------|---------------------------|---------------------|--------------|-----------------------|--------------|
| EN 50363 | Others | ISO 1183 gr/cc | ISO 868 Shore A | ISO 527 N/mm ² | ISO 527 % | ISO 4589 % | CEI 20-34/3-2 Minutes | ISO 458/2 C° |

Transparent grades

| | | | | | | | |
|------------------------|--------------------------------|-------------------|------|----|------|-------|------|
| BZ 81 D | Transparent sheathing | TM2 | 1,21 | 80 | ≥ 18 | ≥ 380 | ≥ 37 |
| BZ 89 D UV | Transparent sheathing anti-UV | TM1 | 1,26 | 89 | ≥ 22 | ≥ 340 | |
| T 89 ATC HT 105 | Transparent insulation (105°C) | UL 1581 Classe 43 | 1,24 | 89 | ≥ 20 | ≥ 330 | |

Bedding

| | | | | | | | |
|------------------------|---|--|------|----|-----|-------|----|
| IN 3080 CZ N | Bedding | | 1,82 | 85 | ≥ 5 | ≥ 200 | |
| IN 3340 AF CZ N | Flame retardant bedding (suggest for CPR application) | | 1,95 | 87 | ≥ 5 | ≥ 180 | 37 |
| IN 92 AF CZ | Flame retardant bedding (suggest for CPR application) | | 1,97 | 92 | ≥ 5 | ≥ 140 | 43 |

Plugs

| | | | | | | | |
|--------------------|--------------------------|--|------|----|------|-------|--|
| SPI 70 A N1 | Plugs injection moulding | | 1,40 | 70 | ≥ 11 | ≥ 300 | |
| SPI 78 A N | Plugs injection moulding | | 1,51 | 78 | ≥ 11 | ≥ 250 | |

STORAGE

These compounds must be stored at ambient temperature (not exceeding 30°) in closed and unbroken packaging in order to avoid exposure to sunlight and water absorption.

Packaging

Available in 25kg plastic bags, carton oktamins or in silos truck

Notes

The values shown in these tables are typical values obtained from measurement made on extruded samples or pressed plates. The information shown in this document should be considered given simply as a guide for the use of the interested product. The technical information shown derive from our laboratory tests and are indicative and not strictly binding. Stir Compounds s.r.l. so will never be considered responsible for the results obtained by using its products in other production processes.



Stir Compounds S.r.l.

Società soggetta all'attività di direzione e coordinamento della STIR S.p.a.

Via Trani 177 - 76121 Barletta (BT) - Italy

Tel. +39 0883 34 18 111 Fax. +39 0883 34 18 300

info@stircompounds.it

www.stircompounds.it